



Calcined Alumina 315 DATA SHEET

Typical Properties:

Appearance:	Fine white powder
Loss on ignition:	<0.3%
BET specific surface area:	1.0 – 2.0 m ² /g
D50:	<3.5 micron
Retained on 20 micron:	5.00% Max

Chemical analysis:

Al ₂ O ₃	>99.50%
SiO ₂	<0.04%
Fe ₂ O ₃	<0.03%
Na ₂ O	<0.40%



Address details

Conradweg 19
2031 CM Haarlem
The Netherlands
Tel +31 (0)23 542 44 16

Contact details

info@keramikos.nl
www.keramikos.nl
KvK 34058053
BTW NL803502382B01

Bank details

NL69 INGB 0003 5221 09
INGB NL2A
NL66 RABO 0324 4610 54
RABO NL2U