



[www.keramikos.nl](http://www.keramikos.nl)

## DATA SHEET

### DRY GROUND BONE ASH – 300 mesh

<u>Chemical</u>	<u>Typical Analysis</u>
SiO <sub>2</sub>	0.60%
TiO <sub>2</sub>	0.01%
Al <sub>2</sub> O <sub>3</sub>	0.12%
Fe <sub>2</sub> O <sub>3</sub>	0.23%
CaO	53.00%
MgO	1.20%
K <sub>2</sub> O	0.08%
Na <sub>2</sub> O	1.03%
P <sub>2</sub> O <sub>5</sub>	39.95%
BaO	0.04%
SrO	0.06%
Passing 300 mesh	>95.0%