

Technical data Fritte 3221 Ground Frit

Technical data

Physical form	Finely ground powder
Fired appearance	Transparent, glossy
Specific gravity	2.74
Typical firing temperature	700 - 1150°C

Typical analysis

Oxide	%
CaO + MgO	40 - 45
B ₂ O ₃	55 - 60

Storage

It is recommended that the product is stored in tightly sealed containers away from direct sunlight at an even temperature in the range of $5 - 35^{\circ}$ C (41 - 95°F).

Under these conditions the material can be stored for reasonable periods, although storage for longer than 12 months is not recommended

Health and safety

Good industrial hygiene and work practices should be adhered to when handling this product.

For detailed health and safety requirements, please consult the appropriate product safety data sheets.

The information and statements herein are believed to be reliable, but no liability for any errors in fact or opinion herein is accepted. It is the sole responsibility of the user to determine the suitability of any information or products referred to herein for their own particular purpose, and Keramikos makes no warranty or representation of fitnessforanyparticularpurpose.