EPK Kaolin



Distributed by: Laguna Clay Company 14400 Lomitas Ave City of Industry, CA 91746 1-800-4Laguna info@lagunaclay.com www.lagunaclay.com

EPK Kaolin is a unique, high quality water washed ceramic kaolin which offers very white fired color, unusually good forming characteristics and high green strength. In glaze, EPK offers excellent suspension capabilities and uncommon cleanliness.

TYPICAL PROPERTIES

CHEMICAL ANALYSIS

SiO2	(%)	45.7
Al ₂ O ₃	(%)	37.4
Fe ₂ O ₃	(%)	0.79
TiO ₂	(%)	0.37
P ₂ O ₅	(%)	0.24
K ₂ O	(%)	0.33
Na _z O	(%)	0.06
CaO	(%)	0.18
MgO	(%)	0.10
LO.I.	(%)	13.9
TYPICAL VALUES		
Moisture	(%)	
	Plus 325 Mesh (Pellet/Prill)	3.0
	Plus 325 Mesh (Airfloated)	1.0
Bulk Density	(lb/ft³)	
	Loose	32
	Packed	46
Dry M.O.R.	(psi)	300
рН		6
M.B.I.	(meq/100g)	3.7

** Soluable SO₄ (ppm) Low - Trace to 150 Med - 150 to 450

Surface Area

Residue

Average Particle Size

325 Mesh Screen

Second Edition

©IMERYS Minerals Ltd 2011

June 2011

Production Site Edgar Plant Country Road 20A Edgar, FL 32149 United States Tel: +1 352 481 2421 Fax: +1 352 481 2334

Commercial Office 1MERYS Minerals 100 Mansell Court East Suite 300 Roswell, GA 30076 United States Tet: +1 770 594 0660 Fax: +1 770 645 3460 Customer Service Number: Tet: +1 800 458 2529

The data quoted are determined by the use of Imerys Standard Test Methods, copies of which will be supplied on request. Every precaution is taken in production to ensure the products conform to our published data. Since the products are based on naturally occurring materials, we reserve the right to change these data should it become necessary. Sales are in accordance with our "Conditions of Sale", copies of which will be supplied upon request.

 (m^2/g)

(µm)

(%)

Pellet (Prill)

Airfloated

25.6

1.0

1.6

1.2